

Formulasi rolling oli dengan bahan dasar minyak jarak (*ricinus communis L*)

Yulianti, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20236840&lokasi=lokal>

Abstrak

Dalam rangka mengurangi ketergantungan terhadap produk minyak pelumas, telah dipelajari formulasi salah satu minyak pelumas untuk metal working, yaitu rolling oil. Bahan dasar yang digunakan adalah minyak jarak (*Ricinus communis L*). Minyak pelumas yang baik adalah memiliki indeks viskositas yang tinggi. Minyak jarak adalah salah satu minyak nabati yang berpotensi dikembangkan menjadi rooling oil karena memiliki indeks viskositas yang tinggi, tetapi nilai tersebut belum memenuhi nilai standar rolling oil yang ada di pasaran. Indeks viskositas minyak jarak adalah 87, sedangkan indeks viskositas rolling oil standar yang ada di pasaran adalah di atas 100.

Dalam penelitian ini dilakukan sintesa rolling oil dengan cara dehidrasi minyak jarak menggunakan katalis campuran natrium bisulfat dan atapulgit Dehidrasi minyak jarak ini menghasilkan rolling oil yang memiliki indeks viskositas 142. Selanjutnya untuk memperbaiki karakteristik rolling oil tersebut dilakukan penambahan aditif antioksidan dan aditif extreme pressure (EP).

Dari hasil penelitian ini diperoleh perbandingan konsentrasi katalis natrium bisulfat dengan atapulgit optimum yaitu 0,5% : 2% (b/b), diperoleh antioksidan dengan konsentrasi terbaik yaitu TBHQ 0,12% dan konsentrasi optimum aditif extreme pressure AP-2337 sebesar 3,5% (b/b).

.....In order to reduce the dependence upon lubricant oil product, it has been studied one of formulation type lubricant oil which is use for metal working namely rolling oil. Castor oil (*Ricinus Communis L*) was used as raw material. The characteristic of good lubricant oil has high viscosity index. Castor oil is one kind of vegetable oil which the potential to be developed for rolling oil due to high viscosity index. Raw castor oil has viscosity index about 83,5 cSt which has not met the market requirement on viscosity index above 100 cSt.

In this study, the synthesis of rolling oil was done by catalysis dehydration using NaHSO₄ and atapulgite. The catalysis dehydration product has viscosity index 142 cSt. The quality was improve by the addition of antioxidant and extreme pressure additive.

The result of the study showed the ratio catalyst concentration NaHSO₄ : atapulgite, 0,5% : 2% (w/w), antioxidant additive was TBHQ 0,12% and extreme pressure additive AP-2337 3,5%.