

Analisa mikrostruktur material magnetik berbasis Nd-Fe-B dan Sm-Co untuk aplikasi magnet permanen hibrida

Siahaan, Mabe, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20277845&lokasi=lokal>

Abstrak

Telah dilakukan preparasi, kajian dan pengamatan struktur mikro sampel magnet hibrid SmCo₅ - Nd₁₂Fe₈₂B₆ setelah melalui proses preparasi teknik metalurgi serbuk. Material hibrid yang dibuat berturut-turut memiliki komposisi stoikiometri yaitu paduan serbuk (Sm,Pr)Co₅ (at.%) dan paduan ingot Nd₁₂Fe₈₂B₆ (at.%). Unsur Dy disubstitusi kedalam Nd-Fe-B sehingga terbentuk paduan fasa Nd_{12-x}Dy_x, Fe₈₂B₆ (at.%) dengan x = 0, 1, 2, 3, 6 dan 9. Selanjutnya, paduan ingot tersebut diproses mil sehingga dihasilkan serbuk halus (Nd,Dy)-Fe-B dengan ukuran partikel 20-40 pm. Kedua serbuk (Sm-Co dan Nd-Fe-B) dicampur dengan perbandingan berat (80+y):(20-y) (wt% } dengan y = 0, 5, 10 dan 15 dan sebagian campuran tersebut dimil dengan waktu yang bervariasi. Serbuk material tersebut dipadatkan melalui pemadatan satu arah dalam cetakan berbentuk silinder sehingga menghasilkan padatan muda. Sampel yang sangat padat dihasilkan setelah menjalani siklus perlakuan panas.

Telah dihasilkan struktur mikro material hibrid yang terdiri dari fasa hibrid (Pr,Nd,Sm,Dy)₂(Fe,Co)₁₄B, (Pr,Nd,Sm,Dy)Co₅ setelah tahapan sinter pada temperatur 1150 °C dan anil pada temperatur 850 °C selama 5½ jam dan diikuti pendinginan cepat kedalam air. Juga telah diamati bahwa 'fasa bingkai' mempunyai tipe 1-5 dan 2-14-1 disamping fasa utama 2-14-1 dan 1-5 dalam material hibrid seperti ditunjukkan oleh SEM-EDS, XRF dan XRD. Struktur mikro tersebut sepertinya berpenampilan 'unik' karena berbeda dengan struktur mikro material magnet konvensional yang berbasiskan Nd-Fe-B atau Sm-Co. Studi dengan SQUID juga dilakukan untuk mengevaluasi sifat magnetik meskipun histerisis loop yang dihasilkan hanya terdapat pada kwadran pertama. Kesimpulan dari penelitian ini adalah bahwa hibridisasi dua fasa magnetik permanen yang berbeda telah memberikan informasi baru yaitu telah dihasilkannya struktur mikro yang 'unik' walaupun fasa-fasa magnetik 1-5 dan 2-14-1 masih tetap dipertahankan sebagai fasa-fasa utama dalam material material hibrid.

<hr>

The preparation, investigation and observation of microstructure of the SmCo₅ - Nd₁₂Fe₈₂B₆ hybride magnetics sample which after preparation processing by powder metallurgy technique have been done. Hybride materials were made of stoichiometry (Sm,Pr)Co₅ (at%) and Nd₁₂Fe₈₂B₆ (at.%) compositions respectively in form of powders and lumps. The element of Dy was substituted into Nd-Fe-B to produces Nd_{12-x} Dy_x, Fe₈₂B₆ (at%) alloys with x = 0, 1, 2, 3, 6 and 9. The alloys were further ball milled to produce fine powders of (Nd,Dy)-Fe-B in the size range of 20-40 μm. Both kinds of powders (Sm-Co and Nd-Fe-B base) were then mixed with ratio (80+y):(20-y) in weight for y = 0, 5, 10 and 15 and successively milled with various milling times. The powder materials were compacted in a silindrieal die and pressed in one direction leads to green compacts. Fully dense compacting samples were obtained after the application of designed heat treatments.

It was found that microstructure for hybrid materials consisted of (Pr,Nd,Sm;Dy)₂(Fe,Co)₁₄B, (Pr,Nd,Sm,Dy)Co₅ obtained after a sintering step at temperature 1150 °C and annealed ata temperature of

850 °C for 5½ hours and followed by quenching into water. It was also observed that a 'frame phase' of 1-5 and 2-14-1 types in addition to the main phase of 2-14-1 and 1-5 in hybrid materials as shown by SEM-EDS, XRF and XRD. This kind of microstructure is assumed unique because different with conventional microstructure of sintered Nd-Fe-B or Sm-Co based materials. The study also employed SQUID to evaluate the magnetic properties despite only first quadrant of the hysteresis loop which available. The conclusion of the current study is that hybridization of two different hard magnetic phases have given new information in that it has produced 'unique' microstructures while the magnetic phases of 1-5 and 2-14-1 still remain as the main phases in hybrid materials.