

## Preparasi dan karakterisasi mikrosfer kitosan suksinat tersambung silang natrium sitrat = Preparation and characterization of microspheres chitosan succinate crosslinked sodium citrate

Andi Adha Yuliani, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20294942&lokasi=lokal>

---

### Abstrak

Mikrosfer merupakan salah satu bentuk sediaan yang banyak diteliti saat ini karena sifat unik yang dimilikinya. Penelitian ini bertujuan untuk membuat dan mengkarakterisasi mikrosfer kitosan suksinat tersambung silang natrium sitrat. Pada penelitian ini mikrosfer kitosan suksinat yang disambung silang dengan sitrat (KS-S) telah berhasil dibuat dengan metode semprot kering dan perbandingan obat-polimer yaitu 1:2. Polimer kitosan suksinat yang digunakan merupakan hasil modifikasi antara kitosan dengan anhidrida suksinat. Mikrosfer kemudian dievaluasi ukuran partikel, bentuk dan morfologi, efisiensi penjerapan, indeks mengembang, efisiensi penjerapan, dan pelepasan obat secara in vitro. Dari hasil penelitian diperoleh, diameter rata-rata mikrosfer KS-S 29,29 m dengan permukaan mikrosfer yang halus dan cekung pada sisinya. Efisiensi penjerapan mikrosfer KS-S sebesar 84,30%. Pelepasan teofilin pada medium asam dari mikrosfer KS-S pada jam ke-2 lebih cepat dibanding pada medium basa dengan nilai masing-masing 82,63% dan 69,24%.

.....Microsphere is one of the dosage form that is currently widely studied because of its unique properties. This study aims to create and characterize chitosan succinate microspheres crosslinked sodium citrate. In this study, micro-spheres chitosan succinctness cross-linked sodium citrate (CS-S) has been successfully prepared by spray drying method and the drug-polymer ratio 1:2. The used chitosan succinctness polymer was the modified-chitosan with succinct an-hydride. Then, the particle size, shape and morphology, entrapment efficiency, swelling behavior, and in vitro drug release of the microspheres were evaluated. Based on the results, the average volume diameter of CS-S was 29,29 m with a smooth and concave surface on the side. The entrapment efficiency of CS-S micro-sphere was 84,30%. The release of theophylline from CS-S microsphere in acidic medium during 2h was faster than that in alkaline medium, which were 82,63% and 69,24%, respectively.