

# Karakterisasi komposit matrik logam AC8A/SiCp yang dibuat dengan metode Hot-Press pada lingkungan atmosfer = Characterization of metal matrix composite AC8A/SiCp processed by Hot-Press method in atmospheric environment

Tika Mustika, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20329065&lokasi=lokal>

---

## Abstrak

Pembentukan komposit matrik aluminium paduan AC8A/SiCp dengan metode hot-press di lingkungan atmosfer yang tidak dikondisikan berpengaruh terhadap karakteristik material yang dihasilkan. Dilakukan analisa terhadap karakteristik matrik terbentuk dan ikatan antar muka matrik dan penguat, untuk melihat pengaruh elemen paduan, lingkungan atmosfer dan parameter proses hot-press terhadap material. Observasi awal parameter proses pembentukan komposit menggunakan serbuk aluminium murni Merck, menunjukkan terbentuknya struktur komposit Al/SiCp yang padat. Perbandingan komposit AC8A/SiCp yang dibuat dengan metode hot-press di lingkungan atmosfer dan metode metalurgi serbuk konvensional dalam ruang vakum, menunjukkan komposit dibuat dengan metode hot-press dengan tekanan 425 MPa, 380oC selama 5 menit, memiliki fasa Al, Si, SiC dengan densitas relatif 99%, dan komposit dibuat dengan metode metalurgi serbuk konvensional pada 600oC selama 6 jam memiliki fasa Al, Si, SiC, Al<sub>2</sub>O<sub>3</sub> dengan densitas relatif 84%. Analisa ikatan antar muka matrik dan penguat melalui pengamatan fraktografi terhadap tiga jenis komposit yang dibentuk dari SiC tanpa pelapis, SiC berlapis MgAl<sub>2</sub>O<sub>4</sub> dan SiC berlapis SnO<sub>2</sub>, menunjukkan terjadinya ikatan antar muka yang baik pada ketiganya, dimana sifat mekanis tertinggi dimiliki komposit dengan SiC tanpa pelapis. Sifat mekanis komposit AC8A/SiCp naik bersamaan meningkatnya fraksi volume penguat, dimana komposit dengan 40% Vf SiCp memiliki kuat tekan 445 MPa, kekerasan 222 HVN.

.....Producing aluminum alloy matrix composites AC8A/SiCp by powder metallurgy of hot-press method under unconditioned atmosphere environments may influence the characteristics of final material. Analysis of characteristics of formed matrix and interfacial bonding between matrix and reinforcement have been done to know about effects of Aluminium alloy elements, atmosphere environment and hot-press parameters. Preliminary observations of process parameters in producing composites using Merck's pure aluminum powder, showed dense structure of formed composites Al/SiCp. Comparative analysis between AC8A/SiCp composites using the hot-press method in unconditioned atmosphere and conventional powder metallurgy with vacuum chamber, showed that hot-pressed using 425 MPa, 380oC in 5 minutes has phase of Al, Si and SiC, with relative density 99%; and using conventional powder metallurgy method with vacuum chamber in 600oC, 6 hours has phase of Al, Si, SiC, with relative density 84%. Interfacial bonding analysis by fractography of three composites : uncoated SiCp, SiCp coated with MgAl<sub>2</sub>O<sub>4</sub> and with SnO<sub>2</sub>, showed that all types has good bonding strength, where uncoated SiCp has highest hardness and compressive strength. Composites hardness and compressive strength are increased along with increasing of reinforcement volume fraction, where 40% Vf SiCp has compressive strength of 445 MPa, hardness of 222 HVN.