

Karakteristik kristalografi dan ferroelektrik lapisan tipis barium zirconium titanate ($BaZrxTi1-xO3$) melalui metode chemical solution deposition = Characterization of crystallographic and ferroelectric of barium zirconium titanate thin films by chemical solution deposition method

Rachmat Andika, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20349647&lokasi=lokal>

Abstrak

Barium Titanate telah diketahui memiliki karakteristik yang dapat dimanfaatkan dalam berbagai aplikasi. Barium Titanate merupakan material dielektrik non-linier yang bebas dari kandungan Plumbum. Konstanta dielektrik dan permitivitas yang tinggi dibandingkan material ferroelektrik lain dan adanya arus bocor yang relatif tinggi menjadikan barium titanate menarik untuk diteliti lebih lanjut. Ion Zirconium merupakan substituent efektif Barium Titanate untuk mengurangi arus bocor dikarenakan ion Zirconium cenderung lebih stabil dibandingkan ion Titanium.

Lapisan tipis barium titanate yang disubstitusi dengan ion Zr(0,08 dan 0,1) dihasilkan melalui metode Chemical Solution Deposition yang dilanjutkan melalui spin coating dan perlakuan panas. Larutan BaZrTiO₃ dideposisikan pada substrat Si hingga 3-5 lapisan dengan kecepatan putar 3000 rpm selama 30 s dilanjutkan dengan pirolisis pada 300°C dan annealing pada 700°C-800°C. Karakterisasi pada lapisan tipis BZT menitikberatkan pada sifat kristalografi melalui XRD dan uji histerisis. Uji histerisis dilakukan dengan sumber tegangan AC dengan 20 Vpp pada frekuensi 60 Hz.

Pola XRD menunjukkan adanya peningkatan ukuran kristalit terbesar pada 800°C sekitar 113 nm dengan menggunakan metode Williamson-Hall. Perbedaan Zr pada struktur BaTiO₃ menggeser bidang hkl pada 2. Dengan jumlah lapisan BaZrTiO₃ meningkat, polarisasi pada histerisis ferroelektrik cenderung tetap.

<hr><i>Barium Titanate is well known materials for many applications. It is nonlinear dielectric material and lead free based material, then this material is environmental friendly. High dielectric constant and permittivity compared with other ferroelectric materials and the high leakage current make barium titanate more interesting for further development. Zirconium ion is effective substituent of Barium Titanate to reduce leakage current. This is possible because Zirconium ion more stable than Titanium ion.

Barium Titanate thin films Zr-doped(0.08 and 0.1 mol) is produced by Chemical Solution Deposition and continued by spin coating and heat treatment. BaZrTiO₃ solution 0.5M is deposited on Si substrate 3-5 layers with rotational speed up to 3000 rpm for 30 s then it was treated by pyrolysis on 300°C and annealing 700°C-900°C. BZT thin films is characterized by XRD to know its crystallographic properties and hysteresis testing. Hysteresis loop is made by using AC voltage source with 20 Vpp at frequency of 60 Hz.

The XRD curves showed that crystalite size, based on Williamson-Hall calculation, is calculated around 113 nm for heat treatment 800°C. The different of Zr substitution in BaTiO₃ structure shifted hkl plane on 2. Multilayer of BaZrTiO₃ films on 0.1 Zr increase saturate polarization and decrease coercive field. In this case ferroelectric properties of BaZrTiO₃ thin films increase, in contrary the low coercive field showed that easily loses its ferroelectric properties.</i>