

# Karakteristik kristalografi dan ferroelektrik lapisan tipis barium zirconium titanate ( $\text{BaZr}_x\text{Ti}_{1-x}\text{O}_3$ ) melalui metode chemical solution deposition = Characterization of crystallographic and ferroelectric of barium zirconium titanate thin films by chemical solution deposition method

Rachmat Andika, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20349647&lokasi=lokal>

---

## Abstrak

Barium Titanate telah diketahui memiliki karakteristik yang dapat dimanfaatkan dalam berbagai aplikasi. Barium Titanate merupakan material dielektrik non-linier yang bebas dari kandungan Plumbum. Konstanta dielektrik dan permitivitas yang tinggi dibandingkan material ferroelektrik lain dan adanya arus bocor yang relatif tinggi menjadikan barium titanate menarik untuk diteliti lebih lanjut. Ion Zirconium merupakan substituent efektif Barium Titanate untuk mengurangi arus bocor dikarenakan ion Zirconium cenderung lebih stabil dibandingkan ion Titanium.

Lapisan tipis barium titanate yang disubstitusi dengan ion Zr(0,08 dan 0,1) dihasilkan melalui metode Chemical Solution Deposition yang dilanjutkan melalui spin coating dan perlakuan panas. Larutan  $\text{BaZrTiO}_3$  dideposisikan pada substrat Si hingga 3-5 lapisan dengan kecepatan putar 3000 rpm selama 30 s dilanjutkan dengan pirolisis pada  $300^\circ\text{C}$  dan annealing pada  $700^\circ\text{C}$ - $800^\circ\text{C}$ . Karakterisasi pada lapisan tipis BZT menitikberatkan pada sifat kristalografi melalui XRD dan uji histerisis. Uji histerisis dilakukan dengan sumber tegangan AC dengan 20 Vpp pada frekuensi 60 Hz.

Pola XRD menunjukkan adanya peningkatan ukuran kristalit terbesar pada  $800^\circ\text{C}$  sekitar 113 nm dengan menggunakan metode Williamson-Hall. Perbedaan Zr pada struktur  $\text{BaTiO}_3$  menggeser bidang hkl pada 2. Dengan jumlah lapisan  $\text{BaZrTiO}_3$  meningkat, polarisasi pada histerisis ferroelektrik cenderung tetap.

Barium Titanate is well known materials for many applications. It is nonlinear dielectric material and lead free based material, then this material is enviromental friendly. High dielectric constant and permitivity compared with other ferroelectric materials dan the high leakage current make barium titanate more interesting for further development. Zirconium ion is effective substituent of Barium Titanate to reduce leakage current. This is possible because Zirconium ion more stable than Titanium ion.

Barium Titanate thin films Zr-doped(0.08 and 0.1 mol) is produced by Chemical Solution Deposition and continued by spin coating and heat treatment.  $\text{BaZrTiO}_3$  solution 0.5M is deposited on Si substrate 3-5 layers with rotational speed up to 3000 rpm for 30 s then it was treated by pyrolysis on  $300^\circ\text{C}$  and annealing  $700^\circ\text{C}$ - $900^\circ\text{C}$ . BZT thin films is charaterized by XRD to know its crystallographic properties and hysteresis testing. Hysteresis loop is made by using AC voltage source with 20 Vpp at frequency of 60 Hz.

The XRD curves showed that crystalite size, based on Williamson-Hall calculation, is calculated around 113 nm for heat treatment  $800^\circ\text{C}$ . The different of Zr substitution in  $\text{BaTiO}_3$  structure shifted hkl plane on 2. Multilayer of  $\text{BaZrTiO}_3$  films on 0.1 Zr increase saturate polarization and decrease coersive field. In this case ferroelectric properties of  $\text{BaZrTiO}_3$  thin films increase, in contrary the low coersive field showed that easily loses its ferroelectric properties.