

# Studi elektrokimia sistem CU AG pada elektroda emas dan platina dan elektrodepositi paduan logam CU AG pada elektroda emas = Electrochemical study of CU AG system on gold and platinum electrode and electrodeposition of cu ag alloy on gold electrode

Mutia Saraswati, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20368612&lokasi=lokal>

---

## Abstrak

Increasing the concentration of CO<sub>2</sub> in the atmosfer had caused main environmental problem recently. Some methods has been applied for reducing concentration of CO<sub>2</sub> in the atmosphere. One of them is using electroreduction for conversion of CO<sub>2</sub> into another chemical compound. Primary key of this electroreduction is using the right catalyst. For this research, catalyst that researcher used is Cu-Ag alloy deposit on gold electrode. The electrochemical characteristic of Cu-Ag system is investigated using cyclic voltammetry. It is resulted that Cu-Ag system has different characteristics on gold and platinum working electrode. Determination of kinetic and thermodynamic parameter of Ag system is calculated using MatLab R2010b program by fitting the simulation voltammogram with experimental voltammogram. The simulation of Ag system on platinum electrode at scan rate 0,1 V/s shows the electrodeposition rate contant (kfp) = 5 x 10-4, transfer coefficient ( $\alpha$ ) = 0,8, formal potential (E<sub>f 0</sub>) = -0,15 V, and diffusion coefficient (D) = 2,25 x 10-5 cm<sup>2</sup>/s. Electrodeposition of Cu-Ag alloys is conducted by chronoamperometry at potential -0,640 V for 10 second. The characterization result of Cu-Ag deposit on gold electrode using XRD shows the Cu peak at 2° = 43,433 and the Ag peak at 2° = 38.191, 44.377, 64.569, and 77.563. The potential reduction of CO<sub>2</sub> which resulted by using Cu-Ag deposit on gold electrode and [BMIM][NTf<sub>2</sub>] is -2,3 V versus Pt electrode.

<hr>Peningkatan konsentrasi CO<sub>2</sub> di atmosfer telah menyebabkan masalah lingkungan utama saat ini. Salah satu metode untuk mengurangi kadar CO<sub>2</sub> di atmosfer adalah konversi CO<sub>2</sub> menjadi senyawa kimia lainnya menggunakan metode elektroreduksi. Kunci keberhasilan dari elektroreduksi CO<sub>2</sub> adalah penggunaan katalis yang tepat. Katalis yang dikembangkan pada penelitian ini adalah deposit paduan logam Cu-Ag pada lempeng emas. Karakteristik elektrokimia sistem Cu- Ag pada elektroda kerja emas dan platina dipelajari menggunakan metode voltametri siklik. Penentuan parameter kinetika dan termodinamika dari sistem Ag dihitung menggunakan program MatLab R2010b dengan cara melakukan fitting voltammogram simulasi dengan voltammogram eksperimen. Hasil simulasi voltammogram sistem Ag pada elektroda platina dengan laju potensial 0,1 V/s adalah tetapan laju elektrodepositi (kfp) sebesar 5 x 10-4, koefisien transfer ( $\alpha$ ) sebesar 0,8, potensial formal (E<sub>f 0</sub>) sebesar -0,15 V, dan koefisien difusi (D) sebesar 2,25 x 10-5 cm<sup>2</sup>/s. Elektrodepositi Cu-Ag dilakukan menggunakan metode kronoamperometri pada potensial -0,640 V selama 10 detik. Hasil karakterisasi deposit Cu-Ag pada lempeng emas memiliki puncak Cu pada 2° sebesar 43,433 dan puncak Ag pada 2° sebesar 38.191, 44.377, 64.569, dan 77.563. Potensial reduksi CO<sub>2</sub> yang diperoleh menggunakan elektroda kerja deposit Cu-Ag pada lempeng emas dan cairan ionik [BMIM][NTf<sub>2</sub>] sebesar -2,3 V terhadap elektroda Pt.