

Sintesis Material Mesopori Fe₂O₃ TiO₂ dari Mineral Ilmenit Bangka sebagai Fotokatalis = The Synthesis of Mesoporous Fe₂O₃ TiO₂ Materials from Bangka-Indonesia Ilmenite as Photocatalyst

Latifa Hanum Lalasari, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20410020&lokasi=lokal>

Abstrak

[ABSTRAK

Indonesia memiliki banyak sumber daya alam ilmenit yang dapat dimanfaatkan lebih lanjut menjadi material mesopori Fe₂O₃ TiO₂. Material mesopori dengan dinding (wall) yang tersusun atas nano-kristalin TiO₂ adalah kandidat yang sangat menjanjikan dalam memberikan sumbangan yang sangat signifikan untuk mengatasi permasalahan lingkungan dan krisis energi yang melanda dunia. Namun demikian, hingga sekarang ini masih sulit untuk memperoleh kombinasi sinergis dua hal utama yaitu susunan pori yang teratur (highly-oriented) dan tingkat kristalinitas yang tinggi.

Penelitian ini bertujuan untuk mensintesis mesopori Fe₂O₃ TiO₂ dari mineral ilmenit (FeTiO₃) untuk aplikasi pemurnian air limbah dan pembuatan prototipe DSSC. Metode yang digunakan dalam penelitian adalah kombinasi teknik hidrotermal dan sol-gel. Tahapan proses adalah mineral ilmenit yang telah dihaluskan dilakukan proses dekomposisi dengan larutan basa dalam autoklaf kemudian dilanjutkan dengan proses pelindian menggunakan asam sulfat. Larutan TiOSO₄ yang dihasilkan digunakan sebagai prekursor dalam mempersiapkan nanopartikel TiO₂ atau material mesopori Fe₂O₃ TiO₂. Pengontrolan dalam proses sol-gel dilakukan dengan penambahan Fe, dextrin dan triblock copolimer. Hasil penelitian dikarakterisasi menggunakan XRF, AAS, TEM/SEM, BET, XRD, DRS, UV Vis.

Hasil penelitian memberikan gambaran tentang potensi yang besar terhadap ilmenit Bangka untuk dimanfaatkan sebagai bahan baku dalam pembuatan material mesopori Fe₂O₃ TiO₂. Ilmenit terdekomposisi dengan pelarut basa (KOH dan NaOH) membentuk fase intermediet yaitu kalium titanat dan natrium titanat dengan morfologi yang berbentuk benang-benang halus.

Penambahan bubuk Fe dan dextrin mampu mengontrol pembentukan nanopartikel dan meningkatkan kemurnian TiO₂. Penelitian ini juga berhasil mempersiapkan mesopori Fe₂O₃ TiO₂ yang digolongkan sebagai bidang kristal anatase maupun rutil dengan ukuran kristal rata-rata berkisar 5 -7 nm, energi band gap berkisar 3,00 ? 3,16 eV dan luas permukaan, SBET berkisar.100 ? 151 m²/g.;

<hr>

ABSTRACT

Indonesia has many natural resources including ilmenite which could be exploited further into mesoporous TiO₂ Fe₂O₃ materials. Mesoporous materials

with walls composed of nano-crystalline TiO_2 are very promising candidate in a very significant contribution for solving environmental problems and energy crisis that hit in the world. However, until now it is still difficult to obtain a synergistic combination of two major things that the regular arrangement of pores (highly oriented) and a high degree of crystallinity.

This study aims to synthesize mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ of the ilmenite (FeTiO_3) mineral for waste water purification applications and prototyping DSSC.

The method used in the study is a combination of hydrothermal and sol-gel techniques. Stage of the process was ilmenite mineral which has been smoothed carried out the decomposition process using alkaline solution in the autoclave and then followed by a leaching process using sulfuric acid. The TiOSO_4 solution obtained was used as a precursor in the preparation of TiO_2 nanoparticles or mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ material. Controlling the sol-gel process was done with the addition of Fe, dextrin and triblock copolymer. The results of the study were characterized using XRF, AAS, TEM/SEM, BET, XRD, DRS, UV-Vis apparatus.

The results of the study provided an overview of the enormous potential of the Bangka-Indonesia ilmenite to be used as raw material in the manufacture of mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ materials. Ilmenite decomposed by alkaline solvent (KOH and NaOH) formed the intermediate phase of potassium titanate and sodium titanate with morphology shaped by fine threads. The addition of Fe powder and dextrin were able to control the formation nanoparticles and increase the purity of TiO_2 . This study also succeeded in preparing mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ classified as anatase and rutile crystal planes with an average crystal size ranges from 5 to 7 nm, the band gap energy ranges from 3.00 to 3.16 eV and the surface area (SBET) ranges from 100 to 151 m^2/g .; Indonesia has many natural resources including ilmenite which could be

exploited further into mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ materials. Mesoporous materials with walls composed of nano-crystalline TiO_2 are very promising candidate in a very significant contribution for solving environmental problems and energy crisis that hit in the world. However, until now it is still difficult to obtain a synergistic combination of two major things that the regular arrangement of pores (highly oriented) and a high degree of crystallinity.

This study aims to synthesize mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ of the ilmenite (FeTiO_3) mineral for waste water purification applications and prototyping DSSC.

The method used in the study is a combination of hydrothermal and sol-gel techniques. Stage of the process was ilmenite mineral which has been smoothed carried out the decomposition process using alkaline solution in the autoclave and then followed by a leaching process using sulfuric acid. The TiOSO_4 solution obtained was used as a precursor in the preparation of TiO_2 nanoparticles or mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ material. Controlling the sol-gel process was done with the addition of Fe, dextrin and triblock copolymer. The results of the study were characterized using XRF, AAS, TEM/SEM, BET, XRD, DRS, UV-Vis apparatus.

The results of the study provided an overview of the enormous potential of the Bangka-Indonesia ilmenite to be used as raw material in the manufacture of mesoporous TiO_2 Fe_2O_3 materials. Ilmenite decomposed by alkaline solvent (KOH and NaOH) formed the intermediate phase of potassium titanate and sodium titanate with morphology shaped by fine threads. The addition of Fe powder and dextrin were able to control the formation nanoparticles and increase the purity of TiO_2 . This study also succeeded in preparing mesoporous TiO_2 Fe_2O_3 classified as anatase and rutile crystal planes with an average crystal size ranges from 5 to 7 nm, the band gap energy ranges from 3.00 to 3.16 eV and the surface area (SBET) ranges from 100 to 151 m^2/g .;Indonesia has many natural resources including ilmenite which could be

exploited further into mesoporous TiO_2 Fe_2O_3 materials. Mesoporous materials with walls composed of nano-crystalline TiO_2 are very promising candidate in a very significant contribution for solving environmental problems and energy crisis that hit in the world. However, until now it is still difficult to obtain a synergistic combination of two major things that the regular arrangement of pores (highly oriented) and a high degree of crystallinity.

This study aims to synthesize mesoporous TiO_2 Fe_2O_3 of the ilmenite (FeTiO_3) mineral for waste water purification applications and prototyping DSSC.

The method used in the study is a combination of hydrothermal and sol-gel techniques. Stage of the process was ilmenite mineral which has been smoothed carried out the decomposition process using alkaline solution in the autoclave and then followed by a leaching process using sulfuric acid. The TiOSO_4 solution obtained was used as a precursor in the preparation of TiO_2 nanoparticles or mesoporous TiO_2 Fe_2O_3 material. Controlling the sol-gel process was done with the addition of Fe, dextrin and triblock copolymer. The results of the study were characterized using XRF, AAS, TEM/SEM, BET, XRD, DRS, UV-Vis apparatus.

The results of the study provided an overview of the enormous potential of the Bangka-Indonesia ilmenite to be used as raw material in the manufacture of mesoporous TiO_2 Fe_2O_3 materials. Ilmenite decomposed by alkaline solvent (KOH and NaOH) formed the intermediate phase of potassium titanate and sodium titanate with morphology shaped by fine threads. The addition of Fe powder and dextrin were able to control the formation nanoparticles and increase the purity of TiO_2 . This study also succeeded in preparing mesoporous TiO_2 Fe_2O_3 classified as anatase and rutile crystal planes with an average crystal size ranges from 5 to 7 nm, the band gap energy ranges from 3.00 to 3.16 eV and the surface area (SBET) ranges from 100 to 151 m^2/g ., Indonesia has many natural resources including ilmenite which could be

exploited further into mesoporous TiO_2 Fe_2O_3 materials. Mesoporous materials with walls composed of nano-crystalline TiO_2 are very promising candidate in a very significant contribution for solving environmental problems and energy crisis that hit in the world. However, until now it is still difficult to obtain a synergistic

combination of two major things that the regular arrangement of pores (highly oriented) and a high degree of crystallinity.

This study aims to synthesize mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ of the ilmenite (FeTiO_3) mineral for waste water purification applications and prototyping DSSC.

The method used in the study is a combination of hydrothermal and sol-gel techniques. Stage of the process was ilmenite mineral which has been smoothed carried out the decomposition process using alkaline solution in the autoclave and then followed by a leaching process using sulfuric acid. The TiOSO_4 solution obtained was used as a precursor in the preparation of TiO_2 nanoparticles or mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ material. Controlling the sol-gel process was done with the addition of Fe, dextrin and triblock copolymer. The results of the study were characterized using XRF, AAS, TEM/SEM, BET, XRD, DRS, UV-Vis apparatus. The results of the study provided an overview of the enormous potential of the Bangka-Indonesia ilmenite to be used as raw material in the manufacture of mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ materials. Ilmenite decomposed by alkaline solvent (KOH and NaOH) formed the intermediate phase of potassium titanate and sodium titanate with morphology shaped by fine threads. The addition of Fe powder and dextrin were able to control the formation nanoparticles and increase the purity of TiO_2 . This study also succeeded in preparing mesoporous $\text{TiO}_2/\text{Fe}_2\text{O}_3$ classified as anatase and rutile crystal planes with an average crystal size ranges from 5 to 7 nm, the band gap energy ranges from 3.00 to 3.16 eV and the surface area (SBET) ranges from 100 to 151 m^2/g .]