

Phase transitions in $\text{La}_{0.73}\text{Ca}_{0.27}\text{Mn}_{1-x}\text{Cu}_x\text{O}_3$ ($0 < X < 0.19$)

Yohanes Edi Gunanto, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20449274&lokasi=lokal>

Abstrak

We have performed resistivity measurements as a function of temperature, with and without an external magnetic field. Magnetization measurements are also done as a function of temperature $M(T)$ as well as a function of an external magnetic field $M(H)$ for $\text{La}_{0.73}\text{Ca}_{0.27}\text{Mn}_{1-x}\text{Cu}_x\text{O}_3$ compounds with $0 < x < 0.19$. The samples with $x = 0$ and 0.06 are insulators. As for the samples with $x = 0.10, 0.13,$ and 0.19 , they undergo an insulator to metal transition as the temperature is lowered. The insulator-metal transition temperatures are $24 \text{ K}, 74 \text{ K},$ and 69 K for $x = 0.10, 0.13,$ and 0.19 , respectively. The magnetoresistance decreases with increasing values of Cu, i.e. $75\%, 72\%, 64\%,$ and 35% for $x = 0, 0.06, 0.10,$ and 0.13 respectively. Samples in accordance with the model of crystalline metal $\ln R$ vs. $1/T$ are compared to Mott insulator models $\ln R$ vs. $1/T^{0.25}$. Based on the magnetization curve, a paramagnetic to ferromagnetic transition is observed at Curie temperature, T_C , of $\sim 196 \text{ K}, 170 \text{ K}, 140 \text{ K}, 137 \text{ K},$ and 113 K for $x = 0, 0.06, 0.10, 0.13,$ and 0.19 respectively.