

Sintesis nanomaterial Bi₂O₃-WO₃ menggunakan ekstrak daun yodium jatropha multifida dan aktifitas fotokatalisisnya terhadap malachite green = Synthesis of Bi₂O₃-WO₃ nanomaterials using yodium leaf extract jatropha multifida and their photocatalytic activity toward malachite green

Nia NurmalaSari, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=20477165&lokasi=lokal>

Abstrak

ABSTRAK

Nanomaterial Bi₂O₃-WO₃ disintesis menggunakan ekstrak daun yodium Jatropha multifida yang mengandung alkaloid sebagai sumber basa dan saponin sebagai surfaktan alami. Nanopartikel hasil sintesis dikarakterisasi dengan X-ray diffraction XRD , Fourier transform infrared FTIR , PSA, Spektrofotometer UV-Visible UV-Vis , Scanning electron microscope SEM , dan Transmission electron microscopy TEM . Karakterisasi dengan XRD menunjukkan bahwa Bi₂O₃ memiliki struktur kristal monoklinik, WO₃ memiliki struktur kristal triklinik, dan nanomaterial Bi₂O₃-WO₃ memiliki struktur tetragonal. Berdasarkan hasil karakterisasi TEM, nanomaterial Bi₂O₃-WO₃ memiliki ukuran 45,58 nm dengan energi band gap sebesar 2,86 eV. Aplikasi aktivitas fotokatalitik malachite green diamati pada daerah sinar tampak. Persentase degradasi malachite green dengan nanopartikel Bi₂O₃, WO₃, dan nanomaterial Bi₂O₃-WO₃ masing-masing adalah 9,24 ; 30,59 ; dan 94,79 selama 2 jam waktu penyinaran.

<hr />

ABSTRACT

Synthesis nanomaterials Bi₂O₃ WO₃ was successfully performed using yodium leaf extract Jatropha multifida with alkaloid for a base source and saponin as biosurfactant. The synthesized nanoparticles and nanomaterials were characterized with X ray diffraction XRD , Fourier transform infrared FTIR , PSA, Spectrophotometry UV Visible UV Vis , Scanning electron microscope SEM , and Transmission electron microscopy TEM . Characterization with XRD shows that nanoparticles Bi₂O₃ have a monoclinic crystal structure, WO₃ have a triclinic crystal structure, and nanomaterials Bi₂O₃ WO₃ have a tetragonal crystal structure. Based on TEM characterization, size of nanomaterials Bi₂O₃ WO₃ is 45.58 nm with band gap energy of 2.86 eV. Activity photocatalytic of application malachite green were observed using visible light radiation. Percentage of degradation malachite green with nanoparticles Bi₂O₃, WO₃, Bi₂O₃ WO₃ nanomaterials were 9.24 30.59 and 94.79 for 2 hours.