

## Synthesis and electrochemical characterization of new $\text{Li}_2\text{O-P}_2\text{O}_5$ compounds for solid electrolytes

Heri Jodi, author

Deskripsi Lengkap: <https://lib.ui.ac.id/detail?id=9999920530844&lokasi=lokal>

---

### Abstrak

The solid electrolyte is of great interest owing to its potential to be applied in a wide variety of electrochemical devices. One of the most stable solid electrolytes is lithium phosphate ( $\text{Li}_3\text{PO}_4$ ). However, this compound has low enough conductivity to be applied to a device such as an electrolyte. A previous study has reported that the mixture of  $x\text{Li}_2\text{O-P}_2\text{O}_5$ , where  $x=2$ , has a greater conductivity than  $\text{Li}_3\text{PO}_4$ , while, when  $x=1$ , this yields an amorphous structure. In this study, new compositions of the  $x\text{Li}_2\text{O-P}_2\text{O}_5$  compounds, where  $1 \leq x \leq 2$ , were prepared through solid-state reactions. The prepared compounds were characterized using X-ray Diffraction Spectrometry (XRD), Scanning Electron Microscopy (SEM), and Electrochemical Impedance Spectroscopy (EIS) measurements in order to investigate their structure, morphology, and electrochemical properties. The XRD characterization showed that both of the samples were composed mainly of  $\text{Li}_4\text{P}_2\text{O}_7$  crystals. Agglomeration of particles was observed in the samples. The conductivity of the compounds was of the order of  $10^{-6}$  S/cm, which was higher by three orders of magnitude than that of  $\text{Li}_3\text{PO}_4$ . The evaluated power exponent of conductivity indicated that the long-range drift of ions may be one of the sources of ion conduction in both of the observed samples. The nature of the dielectric loss indicated that the conduction in the samples was more predominantly DC conduction.